

RE 2521-BN

Normal grade RO element with thick feed spacer for brackish water



AGUA CONTROL LLC
5609 E ADAMO DRIVE STE.D
TAMPA FL, 33619
(813) 621-7774
(813) 621-7776

SPECIFICATIONS :

General Features	Permeate flow rate:	250 GPD (1.1 m ³ /day)
	Stabilized salt rejection:	99.7%
	Effective membrane area:	10 ft ² (0.93 m ²)

1. The stated product performance is based on data taken after 30 minutes of operation at the following test conditions:

- 2,000 mg/L NaCl solution at 225 psig (1.5 MPa) applied pressure
- 8% recovery
- 77 °F (25 °C)
- pH 6.5 -7.0

2. Minimum salt rejection is 99.4%.


3. Permeate flow rate for each element may vary but will be no more than 15%.

4. All elements are vacuum sealed in a polyethylene bag containing 1.0% SBS (sodium bisulfite) solution and individually packaged in a cardboard box.

Membrane type:	Thin-Film Composite
Membrane material:	Polyamide (PA)
Element configuration:	Spiral-Wound, FRP Wrapping

Dimensions

Model Name	A	B	C	D	E	Part Number	
						Inter - connector	Brine Seal
RE 2521 -BN	21.0 inch (534 mm)	2.5 inch (64 mm)	0.75 inch (19.1 mm)	1.1 inch (28 mm)	1.1 inch (28 mm)	4000305	4000223



1. Each membrane element comes with one brine seal, one interconnector (coupler) and four o-rings.
2. All RE2521 elements fit nominal 2.5 inch (64 mm) I.D. pressure vessels.

The information provided in this document is solely for informative purposes. It is the user's responsibility to ensure the appropriate usage of this product. Woongjin Chemical assumes no obligation, liability or damages incurred for the misuse of the product or for the information provided in this document. This document does not express or imply any warranty as to the merchantability or fitness of the product.

RE 2521-B N

Normal grade RO element with thick feed spacer for brackish water



APPLICATION DATA :

Operating Limits	· Max. Pressure Drop / Element	15 psi (0.1 MPa)
	· Max. Operating Pressure	600 psi (4.14 MPa)
	· Max. Feed Flow Rate	6 gpm (1.36 m ³ /hr)
	· Min. Concentrate Flow Rate	1 gpm (0.23 m ³ /hr)
	· Max. Operating Temperature	113 °F (45 °C)
	· Operating pH Range	2.0–11.0
	· CIP pH Range	1.0–13.0
	· Max. Turbidity	1.0 NTU
	· Max. SDI (15 min)	5.0
	· Max. Chlorine Concentration	< 0.1 mg/L
Design Guidelines for Various Water Sources	· Wastewater Conventional (SDI < 5)	8–12 gfd
	· Wastewater Pretreated by UF/MF (SDI < 3)	10–14 gfd
	· Seawater, Open Intake (SDI < 5)	7–10 gfd
	· Seawater, Beach Well (SDI < 3)	8–12 gfd
	· Surface Water (SDI < 5)	12–16 gfd
	· Surface Water (SDI < 3)	13–17 gfd
	· Well water (SDI < 3)	13–17 gfd
	· RO permeate (SDI < 1)	21–30 gfd
Saturation Limits (Using Antiscalants) †	· Langelier Saturation Index (LSI)	< +1.5
	· Stiff and Davis Saturation Index (SDSI)	< +0.5
	· CaSO ₄	230% saturation
	· SrSO ₄	800% saturation
	· BaSO ₄	6,000% saturation
	· SiO ₂	100% saturation

†The above saturation limits are typically accepted by proprietary antiscalant manufacturers. It is the user's responsibility to ensure proper chemical(s) and concentration are dosed ahead of the membrane system to prevent scale formation anywhere within the membrane system. Membrane elements found or damaged due to scale formation are not covered by the limited warranty.

GENERAL HANDLING PROCEDURES

- ▣ Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40–95°F) and should not be stored in direct sunlight. If the polyethylene bag is damaged a new preservative solution (sodium bisulfite) must be added and airtight sealed to prevent drying and biological growth.
- ▣ Permeate from the first hour of operation should be discarded to flush out the preservative solution.
- ▣ Elements should be immersed in a preservative solution during storage, shipping and system shutdowns to prevent biological growth and freezing. The standard storage solution contains 1% by weight sodium bisulfite or sodium metabisulfite (food grade). For short term storage (i.e. one week or less) 1% by weight sodium metabisulfite solution is adequate for preventing biological growth.
- ▣ Keep elements moist at all times after initial wetting.
- ▣ Avoid excessive pressure and flow spikes.
- ▣ Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.
- ▣ Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.



AGUA CONTROL LLC
5609 E ADAMO DRIVE STE. D
TAMPA FL, 33619
(813) 621-7774
(813) 621-7776